


elasto 250113 Release: 1 Page: 1 of 8

7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57





1. Table of Contents

- 1. Table of Contents
- 2. Application Analysis Data
 - 2.1 Calculated Results in Compression and Shear
 - Example Application
- 3. Recommended Compression Load
- 4. Recommended Shear Load
- 5. Compression/Injection Molded Standard Product Tolerances
- 6. Rubber Selection
- 7. Tightening Torque and Bolt Grades & Class
- 8. Torque Threaded Stud Test of elasto-A- and B-Mounts
- 9. Certificate of RoHS compliance and shelf life expectancy.




elasto 250113 Release: 1 Page: 2 of 8


7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57










elasto 250113 Release: 1 Page: 3 of 8

7525AF38


elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57





3. Recommended Compression Load




?

Compression Deflection Information

0.000 2183.2

> ? Natural Frequency at max. load ?Isolation at



Calculated Isolation




elasto 250113 Release: 1 Page: 4 of 8

7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57





4. Recommended Shear Load


Shear Information

Deflection	0.000
Spring Rate	246
max. stress	0.21

Shear Deflection Information 0.000

245.8

? Natural Frequency by max. load ? Isolation by



Loaded




elasto 250113 Release: 1 Page: 5 of 8

7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57





5. Compression/Injection Molded Standard Product Tolerances

Standard compression molded product dimensional tolerances conform to DIN ISO 3302-1 M3 C Standard Injection molded product tolerances conform to DIN ISO 3302-1 M3 F Further information regarding product/process guality can be provided upon request.

	Dimensions Dimensions mm inch		Tolerance in mm Class M3-F DIN ISO 3302-1	Tolerance in Inch Class M3-F DIN ISO 3302-1	Tolerance in mm Class M3-C DIN ISO 3302-1	Tolerance in Inch Class M3-C DIN ISO 3302-1	
from	to	from	to	mm	inch	mm	inch
0	4	0	.15"	± 0.25	±.010	±0.40	±.016
4	6.3	.16"	.25"	± 0.25	± .010	± 0.40	± .016
6.3	10	.25"	.39"	± 0.30	±.012	± 0.50	±.020
10	16	.39"	.63"	± 0.40	±.016	±0.60	±.024
16	25	.63"	.98"	± 0.50	±.020	±0.80	±.032
25	40	.98"	1.57"	± 0.60	±.024	± 1.00	±.040
40	64	1.57"	2.52"	± 0.80	±.032	± 1.30	±.051
63	100	2.38"	3.94"	± 1.00	±.040	± 1.60	±.063
100	160	3.94"	6.30"	± 1.30	±.051	± 2.00	±.079
160		6.30"		± 1.3 %	± 1.3 %	± 1.3 %	± 1.3 %

Standard rubber hardness tolerance ± 5 Shore A Durometer per ASTM D2000




elastometall Ky LLC • +1 (502) 871-4422 www.elastometall.com Product Specification/ Certificates and Assembly Instruction elasto 250113 Release: 1 Page: 6 of 8

7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57





6. Rubber Selection

	Ê.	(.			1 - <u></u>							PRO	PER	TIES					
Hardness Range (ShoreA)	Temperature Resistance Range 'C (F*)	Short Term Peak Temperature C° (F°)	Tensile Strength (N/mm ²⁾ (PSI)	Tensile Eloangariotion %	Elastomer Basic Material Chemical-Technical Discription Below: (Trade Name)	International Description	Tensile Strength	Tear Resistance	Abrasion Resistance	Restoring Ability	Rebound Resilience	Ozone Resistance	Flame Resistance	Acid Resistance	Benzene & Mineral Oil Resistance	Gas Impermeability	Water Absorption Resistance	- Temperature Resistance	+ Temperature Resistance
25 - 95	-40°- 75° (-40°- 167°)	+100° (212°)	31 (4496)	800	Natural Rubber	NR	2	2	2	2	1	4	5	3	5	4	3	2	4
30 - 90	-30°- 120° (-22°- 248°)	+150° (302°)	27.5 (3988)	450	Chloroprene (Baypren, Neoprene)	CR	2	3	2	3	2	2	2	2	3	3	4	4	3
30 - 90	-40°- 150° (-40°- 302°)	+180° (356°)	20 (2901)	450	Ethylene-Propylene - Terpolymer	EPDM	3	4	3	3	3	1	6	3	5	3	2	3	2
25 - 95	-40°- +140° (-40°- 248°)	+160° (320°)	25 (3626)	500	Ntrile Butadine (Perbunan)	NBR	3	4	3	3	3	5	5	3	1	3	3	4	3
35 - 95	-30°- +110° (-22°- 230°)	+150° (302°)	25 (3626)	450	Styrene-Butadiene	SBR	3	3	2	3	3	5	5	3	5	3	3	3	3
30 - 85	-40°- +130° (-40°- 266°)	+150° (302°)	17 (2466)	800	Butyl	IIR	3	2	2	3	5	1	4	4	6	4	2	2	3
55 - 98	-30°- +80° (-22°- 176°)	+100° (212°)	30 (4351)	800	Polyurethane	PUR	1	2	1	3	3	2	4	5	2	4	5	3	4
40 - 80	-70°- +180° (-94°- 356°)	+225° (437°)	8 (1160)	250	Silicone Rubber	SI	5	5	5	5	2	1	4	3	5	5	4	1	1
65 - 90	-30°- +225° (-22°- 437°)	+350° (662°)	20 (2901)	400	Fluorocarbon (Viton)	FPM	3	2	5	5	4	1	1	1	1	1	2	4	1

The above mentioned information are used for a guide and can be modified by elatometall to improve certain characteristis.

Printed On: 11/14/17, 10:55:51 am




elasto 250113 Release: 1 Page: 7 of 8

7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57





7. Tightening Torque and Bolt Grades & Class

Tightening Torque per ASTM A193 and A194

Metric	Metric Units: (Metric Thread)				English Units: (Coarse Thread)				English Units: (Fine Thread)						
	CLASS 5.6	GRADE 2 GRADE 5 GRADE 8			GRADE 2	GRADE 5	GRADE 8								
Thread Size & Pitch	Tightening Torque (Nm)	Tightening Torque (Nm)	Tightening Torque (Nm)	Thread Size & Pitch	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)	Thread Size & Pitch	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)				
M2	0.16	0.37	0.52	6-32	0.86	1.33	1.88	6-40	0.96	1.49	2.1				
M2.3	0.26	0.6	0.84	8-32	1.58	2.44	3.44	8-36	1.66	2.57	3.63				
M2.6	0.37	0.86	1.21	10-24	2.29	3.53	499	10-32	2.61	4.04	5.7				
M3	0.59	1.34	1.88	12-24	3.59	5.55	7.84	12-28	3.83	5.92	8.36				
M3.5	0.9	2.06	2.89	1/4-20	5.47	8.45	11.9	1/4-28	6.26	9.7	13.7				
M4	1.34	3.04	4.31	5/16-18	11.3	17.4	24.6	5/16-24	12.5	19.3	27.2				
M5	2.65	6.03	8.48	3/8-16	20	30.9	43.6	3/8-24	22.66	35	49.4				
M6	4.51	10.3	14.71	7/16-14	32	39.4	69.8	7/16-20	35.7	55.2	77.9				
M7	7.45	17.16	24.52	1/2-13	48.8	75.4	106	1/2-20	55	84.9	120				
M8	10.79	25.5	35.3	9/16-12	70.4	109	154	9/16-18	78.5	121	171				
M10	21.57	50.01	70.61	5/8-11	97.1	150	212	5/8-18	110	170	240				
M12	38.25	87.28	122.58	3/4-10	103	366	376	3/4-16	115	297	420				
M14	60.8	138.27	194.17	7/8-9	167	430	606	7/8-14	184	473	668				
M16	93.16	210.84	299.1	1-8	250	561	909	1-12	273	613	995				
M18	127.49	411.88	411.88	1-1/8-7	354	794	1288	1-1/8-12	397	891	1445				
M20	180.44	558.98	578.5	1-1/4-7	500	1120	1817	1-1/4-12	553	1241	2012				
M22	245.17	558.98	784.54	1-3/8-6	655	1469	2382	1-3/8-12	746	1673	2712				
M24	308.91	710.99	1000.28	1/2-6	869	1949	3161	1-1/2-12	978	2194	3557				
M27	460.92	1049.32	1480.81												
M30	522.73	1421.97	2010.38												

Non-Standard




elasto 250113 Release: 1 Page: 8 of 8

7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57






8. Torque Threaded Stud Test of elasto-A- and B-Mounts

Tighten flat bar steel on jaw vise. Setup required torque wrench per table. Use a nut for specimen and tighten it with torque wrench until the required torque is achieved. Loosen nut from specimen and visual check threaded studs for:

- Stud extension

- Thread pitch damaged or sheered
- Connection between washer
- Broken stud






elasto 250113 Release: 1 Page: 9 of 8

7525AF38

elasto-A-Mounts 75x25 75x25 A UNF1/2-20/25 Shore A

Dimensions:	
D	Н
2.95	0.98
G1	G2
UNF1/2-20	UNF1/2-20
L1	L2
0.98	0.98
Elastomer	ShoreA
	57





9. Certificate of RoHS Compliance

Customer

We confirm that these mounts are RoHS Compliance.

9. Shelf Life Expectancy

Rubber to metal bonded products have a shelf life expectancy of up to 20 years under certain conditions such as room temperature and avoiding direct sunlight or artificial lights.

- ALWAYS KEEP PARTS AWAY FROM DIRECT SUNLIGHT AND BETWEEN 10° - 30° CELSIUS -